


with storage solution




- Type** Braided and coated multifilament
- Composition** Polyglycolic acid
- Coating** Polycaprolactone and calcium stearate (1%)
- Colour** Violet
- Tissue reaction** Minimal
- Absorption** The hydrolytic action by which the material is broken down results in total absorption in approximately 60 to 90 days. Approximately 50% of tensile strength remain after 21 days.


Benefits of this especially adapted storage solution:

- better protection against potential contamination
- passes better through tissues
- softer thread
- Synthetic absorbable
- Braided multifilament
- Breaks down by hydrolysis
- Indications:
Muscles, connective tissue, skin, etc.

ABSORPTION



TENSILE STRENGTH



TENSILE STRENGTH IN NEWTONS

Metric	USP	Newtons
1.5	4/0	15
2	3/0	26
3	2/0	42
3.5	0	52
4	1	68
5	2	94
6	3&4	120
7	5	153
8	6	173

IN CASSETTES

Use within 4 months after first opening

Metric	USP	Length	Order number
1.5	4/0	15 m	15151
2	3/0	15 m	15201
2	3/0	25 m	15202
3	2/0	15 m	15301
3	2/0	25 m	15302
3	2/0	50 m	15305
3.5	0	15 m	15351
3.5	0	25 m	15352
3.5	0	50 m	15355
4	1	15 m	15401
4	1	25 m	15402
4	1	50 m	15405
5	2	15 m	15501
5	2	25 m	15502
5	2	50 m	15505
6	3&4	15 m	15601
6	3&4	25 m	15602
6	3&4	50 m	15605
7	5	15 m	15701
7	5	25 m	15702
7	5	50 m	15705
8	6	15 m	15801
8	6	25 m	15802
8	6	50 m	15805