


# SURGICRYL<sup>®</sup>

## MONOFAST

### POLYGLECAPRONE 25



<b>Type</b>	Monofilament
<b>Composition</b>	Polyglecaprone 25, a copolymer made of 75% glycolide and 25% ε-caprolactone
<b>Coating</b>	None
<b>Colour</b>	Violet / Beige - undyed
<b>Tissue reaction</b>	Minimal
<b>Absorption</b>	The hydrolytic action by which the material is broken down results in total absorption in approximately 90 to 120 days. Approximately 60% of tensile strength remain after 7 days.
<b>Presentation</b>	Box with 12 sutures



*For quality  
&  
safety*

[www.sutures.be](http://www.sutures.be)

# SURGICRYL<sup>®</sup>

## MONOFAST

### POLYGLECAPRONE 25

#### CHARACTERISTICS

- High tensile strength
- Synthetic
- Breaks down by hydrolysis
- Monofilament with microscopic uniform diameter
  
- Pliability and softness
- Hermetically sealed packing

#### BENEFITS

- Excellent tissue support
- Minimal tissue reaction
- Predictable absorption rate
- Soft passage through the tissues without sawing, tissue drag and trauma
- Absence of capillarity (no support of bacterial growth)
- Excellent knot tie down
  
- Good handling properties
- Easy and secure knotting
  
- Guaranteed seal and product sterility


**INDICATIONS** Superficial soft tissue and/or ligation  
 especially in General surgery  
 Skin closure  
 Plastic surgery  
 Gastrointestinal surgery  
 Gynaecology  
 Urology

**CONTRAINDICATIONS** Cardiovascular surgery  
 Neurosurgery  
 Ophthalmic surgery


Being absorbable not to use when an extended wound support is required.

Caution in patients with delayed wound healing (e.g. compromised immune system).

#### TENSILE STRENGTH



#### ABSORPTION



### IN CASSETTES

Use within 3 months after first opening

Metric	USP	Length	Order number
1.5	4/0	15 m	16151
2	3/0	15 m	16201
2	3/0	25 m	16202
3	2/0	15 m	16301
3	2/0	25 m	16302
3.5	0	15 m	16351
3.5	0	25 m	16352
4	1	15 m	16401
4	1	25 m	16402
4	1	50 m	16405
5	2	15 m	16501
5	2	25 m	16502
5	2	50 m	16505
5	2	100 m	165010
6	3&4	15 m	16601
6	3&4	25 m	16602
6	3&4	50 m	16605

